

200g / Item no.101001 / EAN 4016215101001

1kg / Item no.101018 / EAN 4016215101018



Ready-to-use, solvent-free wood putty for repairing damaged wooden surfaces. Can be applied easily and cleanly and hardens evenly and without cracks both inside and out.

- Natural colour
- tintable
- Quick drying
- solvent-free
- for indoors and outdoors

Area of application

For quickly filling and smoothing cracks, holes, joints, slits and damaged edges on windows, doors, steps, furniture and other wooden objects.

Preparation

The substrate must be clean, dry, level, sound, absorbent and free of release agents. Substrates that cannot be consolidated or do not adhere sufficiently must be completely removed. If in doubt, carry out a test application.

Processing

Stir well before use. Apply with a spatula, trowel, etc. The filler hardens without cracking up to a layer thickness of 5 mm. For thicker coats, apply several coats after the previous coat has dried. Clean tools with water immediately after use. After drying, the wood putty can be easily machined (sanded, drilled) and treated with stains and paints. We recommend sanding the surface slightly before staining. Drying time: approx. 24 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions. Tinting: With max. 10% suitable universal tinting concentrates.

Consumption

per mm layer thickness → approx. 1.4 kg/m²

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Processing temperature: +5 °C to +30 °C for material, ambient air and substrate. Keep out of reach of children. Ensure adequate ventilation during application and drying. Avoid eating, drinking and smoking while using the paint. Wear safety goggles. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.